



TECHNICAL INFORMATION

SEGASOFT HK liq

Hydrophilic Softener

- Slightly cationic hydrophilic softener, especially developed for towel, underwear etc.
- It provides soft touch and draping.
- Suitable for white products, does not cause yellowing.
- It does not disrupt the hydrophilicity of fabrics and improve the hydrophilicity.

PROPERTIES

Chemical Structure	Polysiloxane compound and special components
Appearance	White liquid
Ionic structure	Slightly cationic
pH	3.0-5.0
Solubility	Soluble in water in any ratio

APPLICATION

Foulard method

10- 50 g/L Segasoft HK Liq

pH: 4.5 - 5.5

Pick-up:~70-80%

Fixed temperature 130 - 150°C

Exhaust method

% 1-5 Segasoft HK Liq

pH: 4.5 - 5.5

Temperature: 40 - 50°C

Duration: 20-30 min.

Fixed temperature 130 - 150°C

Storage and handling

Suitable storage condition is 12 months in closed containers.

(Sensitive to freezing and temperatures above 40°C)

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet.