



TECHNICAL INFORMATION

SOFTEN SLP Eco Liq

Micro silicone emulsion

- It used to obtain a good touch in cotton products which are especially hard to soften.
- Provides comfortable operation in physical finishing processes (raising, brush, etc.) by staying on the surface.
- It has low thermal yellowing effect on fabric
- Suitable for use in foulard systems.
- It does not cause sticking problems on foulard.

PROPERTIES

Chemical Structure	Silicone emulsion
Appearance	Clearly liquid
pH	5.0–7.0
Ionic Character	Slightly cationic
Solubility	Soluble in water in any ratio

APPLICATION

Application amounts varies depending to desired final hand-feeling.

Foulard Method

20–60 g/L Soften SLP Eco Liq

pH: 4.5–5.5

Pick-up:~70–80%

Drying & Curing: 130–150°C

Storage and handling

Suitable storage condition is 12 months in closed containers.

(Sensitive to freezing and temperatures above 40°C)

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet.