



TECHNICAL INFORMATION

SEGASOFT KTY Liq

Segasoft KTY liquid is a non-yellowing and cationic softener which is extremely effective on natural, synthetic, blend fibers, and fabrics

- It is used to provide softness and elasticity for cotton and synthetic fabrics and their blends.
- Yellow tendency is low.
- Segasoft KTY Liq; is suitable for exhaust and foulard systems.

PROPERTIES

Chemical Structure	Fatty acid condensation product
Appearance	Creamy liquid
pH	4.0–6.0
Ionic Character	Cationic

APPLICATION

Foulard Method

10–50 g/L Segasoft KTY Liq

pH: 4.5–5.5

Pick-up: ~ 70–80%

Fixing Temperature: 130–150°C

Exhaust Method

1–5% Segasoft KTY Liq

pH: 4.5–5.5

Temperature: 40–50°C

Duration: 20–30 min

Fixing Temperature: 130–150°C

Storage and handling

Suitable storage condition is 12 months in closed containers.

(Sensitive to freezing and temperatures above 40°C)

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet.