



TECHNICAL INFORMATION

SEGAGUARD SBY

Synthetic and cellulosic textile products, especially cotton, polyester and their blends is used in water and oil repellent finishing product

- Segaguard SBY is used in water and oil repellent finishings of synthetic and cellulosic textile products, especially cotton, polyester and their blends.
- Segaguard SBY gives the product a bulkiness handle.
- Segaguard SBY is highly wash resistant.
- Segaguard SBY shows low sensitivity to residues on the product.
- It is recommended to prepare the finishing bath with soft water.

PROPERTIES

Chemical Structure	C6 fluorocarbon polymer
Appearance	Slightly yellow milky liquid
pH	4.0-6.0
Solubility	Soluble in water in any ratio

APPLICATION

Foulard Method

100% PA or PES

30 – 60 g/L Segaguard SBY

100% Cotton

40 – 80 g/L Segaguard SBY

Pick-up: ~ 65 – 80%

Fixing Temperature: 150 – 170°C, 1 – 3 min.

Storage and handling

Suitable storage condition is 12 months in closed containers.

(Sensitive to freezing and temperatures above 40°C)

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet