

Levasol Red 6G

Short Profile

- Yellowish red with very highlight fastness. Main trichromatic red dye in combination with LEVASOL Yellow 4G and LEVASOL Blue 3G

Substrate Suitability :

Polyamide	M
Wool	S
Silk	S


General properties:

Solubility at 90°C (g/l)	100
Dischargeability (Zn Sulfoxylate Formaldehyde)	2-3


Shade change under article light:

D65	Inc A	F11 (TL 84)
Control	M.Yelllowr/.R./ Brightre	Yelllowr/ Brightre



Cross staining on other components of blends in one bath dyeing :



Exhaustion Fixation :



Saturation Curve:



(Exhaust Dyeing on Wool fabric at 98°C for 45 min pH 4 with Formic Acid)


(This information is provided in good faith, to the best of our knowledge and without liability)

Fastness Properties Details

Levasol Red 6G	Wool Fabric			
Light Fastness Shade depth	1/12	1/6	1/3	1/1
Light fastness (ISO 105 B02)- Upto grade 6	5.6	6	6	6
Light fastness (AATCC 16E) 20 AFU	4.5	4.5	4.5	4.5
Light fastness (AATCC 16E) 40 AFU	4	4	4	4

Wet Fastness properties on 1/1 SD	SC	WO	PA	CO
Wash fastness (ISO 105 C10 - B (50 ^o C)	4.5	4.5	5	4.5
Wash fastness (ISO 105 C10 - C (60 ^o C)	4.5	4.5	4.5	5
Wash fastness (AATCC 61 Option 2A,49 ^o C,)	4.5	4.5	5	5
Home laundry ISO 105 C06 B2S 50 ^o C	4.5	5	5	5
Fastness to Hot water ISO 105 E08 70 ^o C	4.5	4	*	5
Fastness to Sea Water (ISO 105 E02)	4.5	4.5	4	4.5
Water Fastness Sever (ISO 105 E01)	4.5	4.5	4.5	4.5
Perspiration fastness (ISO 105 E04)	Acidic	4.5	4.5	5
	Alkaline	4.5	4.5	5
Fastness to alkaline milling,sever ISO 105- E012	4.5	4.5	4.5	4.5
Fastness to acid millingmild ISO 105- E014	4.5	4.5	4.5	4.5
Fastness to cross - dyeing acetic acid ISO 105 E07	3	3	*	4-5
Shampoo Fastness woolmarkTM233	4.5	4.5	4.5	4.5
Fastness to Potting ISO 105 E09	3.4	3-4	*	5
Fastness to chlorination acid ISO 105 X03	3	4	4.5	4.5

Fastness to ISO 105 XE02 carbonizing (COS)	4	neutralized	4		
Fastness to decatizing sever ISO 105 E10 (COS)	4				
Fastness to formaldehyde ISO 105 X09 (COS)	3.4				
Fastness to acid spotting ISO 105 E05	Acetic acid	4-5	4-5	*	5
	Sulphuric acid	4	4-5	*	5
Crocking Fastness (ISO 105 X12)	Dry	4.5	Wet	4	



Remarks:-

(COS = Change of Shade , WO = Staining on Wool , PA = Staining on Polyamide , CO = Staining on Cotton,)