


Coralene Blue 2R Conc.

A medium energy royal blue disperse dye suitable for general dyeing and printing applications on polyester

Suitability / Application:		
<u>Substrate:</u>		
Fiber / Yarn	-	÷
Sewing threads	-	•
Piece dyeing	-	•
Micro fibers / fabric	-	
P/C Blends - Exhaust, 2 bath	-	
P/C Blends - Continuous	-	
P/Elastane Blends	-	
P/W Blends	-	0
Process:		
Exhaust dyeing:		
Low temperature with carrier	-	0
Carrier dyeing at 110 ⁰ C	-	0
HT, 130 ⁰ C	-	•
HT, Alkaline dyeing (buffered at pH	19.5)	0
Continuous dyeing	-	
<u>Printing</u>	-	•
Development method in printing:		
Pressure Steaming	-	•
HT Loop Steaming	-	•
Discharge printing	-	
Dischargeable ground	-	•
Discharge resistant illuminant	-	0



General properties:

C.T.Z.:	110° - 130°C	Continuous dyeing
Leveling at 130 ⁰ C:	Moderate	27.0 g/l on P/C cloth
Migration:	Moderate	
pH range for application :	4.0 - 6.0	
Dischargeability:(Zinc sulphoxylate formaldehyde)	Good	
Sensitivity to metal (Fe):	Low	
Stripping method:	Reductive	
Saturation value in HTHP exhaust dyeing:	5.50%	
(On 80D/36F polyester knit fabric)		

Shade change under artificial light:	D 65	Inc A	F 11 (TL 84)	F02 (CWF)	UL 35
	Control	Y	RR	RR	R

Cross staining on other components of blends in one bath dyeing:

Substrate	CA	PAN	PA	Cellulosic	Wool
Staining in dyebath	High	Moderate	High	Moderate	High
Staining after R.C.	High	Moderate	High	Moderate	Moderate


(Abbreviation: ● - Suitable, ○ - Not Suitable, ● - Limited suitability, ■ - Not Recommended, R - Redder,

G - Greener, B - Bluer)




Coralene Blue 2R Conc.

Product Performance:




(Dyeing at different dyebath temperature on polyester fabric at pH 4 adjusted with Levocol 4398)



(Exhaust dyeing different depth at 130[°]C temperature for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)


Thermosol Application:

27.0 gpl Coralene Blue 2R Conc on P/C fabric



pH Sensitivity:

2.70 % Coralene Blue 2R Conc in exhaust dyeing



Fastness Properties: (Tested on 80D/36F 100% PET Knit dyed by exhaust method)

		Shade change (Rating)		
		1/6 SD	1/3 SD	1/1 SD
 Light fastness (ISO 105 B02) 		4	4	5-6
 Light fastness (AATCC 16, Option 3, 20 AFU) 		3.5	4.0	4.0
• Sublimation fastness 1/1 SD (ISO 105 P01, 30 Sec)	Temperature	180 ⁰ C	190 ⁰ C	200 ⁰ C
	C.O.S.	4	4	4
	Staining on PET	3-4	3	2-3
V 1.0,07/20				Page 2 of 3



Coralene Blue 2R Conc.

Fastness Properties: (Tested at 2.70 % depth, on 80D/36F 100% PET Knit dyed by exhaust method and post set at 180⁰C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
 Perspiration Light fastness (ISO 105 B07) 	Acidic	4-5						
 Perspiration Light fastness (ISO 105 B07) 	Alkaline	4-5						
 Wash fastness (ISO 105 C06, A2S,) 		4	4	4-5	3-4	4	4-5	4-5
 Wash fastness (ISO 105 C06, C2S,) 		4	3-4	4	2-3	3	4	4
 Wash fastness (ISO 105 C10 C, 60⁰C) 		4	4	4-5	3-4	4	4-5	4-5
▶ Wash fastness (AATCC 61 Option 2A, 49 ⁰ C)		4.0	3.5	4.5	2.5	3.0	4.5	3.5
 Dry cleaning fastness (ISO 105 D01) 		4	4-5	4-5	4-5	4-5	4-5	4-5
Water fastness (ISO 105 E01)		4-5	4-5	4-5	4	4-5	4-5	4-5
Sea water fastness (ISO 105 E02)		4-5	4-5	4-5	4	4-5	4-5	4-5
Chlorinated water (ISO 105 E03)	20 ppm	4-5						
Chlorinated water (ISO 105 E03)	50 ppm	4-5						
Perspiration fastness (ISO 105 E04)	Acidic	4-5	4-5	4-5	4	4-5	4-5	4-5
Perspiration fastness (ISO 105 E04)	Alkaline	4-5	4-5	4-5	4	4-5	4-5	4-5
Hypochlorite bleach fastness (ISO 105 N01)		4						
Peroxide bleach fastness (ISO 105 N02)		4		4-5		4		
Crocking fastness (ISO 105 X12, Dry/Wet)				4-5/4-5				
 PVC migration (ISO 105 X10) 		2-3	(Staining or	n PVC film)				
 Saliva fastness (DIN 53160) 		5.0	5.0 (Staining on filter paper)					

Note:

Disclaimer: This information is provided in good faith, to the best of our knowledge and without liabilities.



Colourtex Industries Private Limited, = COLOUTECX 91, Bhestan, Surat - 395023 (India) The Dyestuff Company Domestic: Tel.: +91 261 2897800/2 Domestic: Tel.: +91 261 2897800/2897801 E mail: sales.surat@colourtex.co.in Export: Tel.: +91 261 2891427 /2897428

E mail: ctx.export@colourtex.co.in

V 1.0,07/20