


# **Coralene Blue SBGL**

A high energy non dischargeable blue disperse dye suitable for high light fastness applications and colour discharge printing on polyester


#### **Suitability / Application:**

# Substrate:



**Exhaust Dyeing** 

#### **Process:**



(Dyeing at 130°C for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)

#### 1.80%



# **General properties:**

C.T.Z.:	110 - 130 <sup>0</sup> C
Leveling at 130 <sup>0</sup> C:	Moderate
Migration:	Moderate
pH range for application :	3.0 - 8.0
Dischargeability:(Zinc sulphoxylate formaldehyde)	Non dischargeable
Sensitivity to metal (Fe):	Low
Stripping method:	-
Saturation value in HTHP exhaust dyeing:	2.00%
(On 80D/36F polyester knit fabric)	



#### Shade change under artificial light:

D 65	Inc A	F 11 (TL 84)	F02 (CWF)	UL 35
Control	R	RR	RR	RR

# Cross staining on other components of blends in one bath dyeing:

Substrate	CA	PAN	PA	Cellulosic	Wool
Staining in dyebath	High	Moderate	High	Moderate	High
Staining after R.C.	High	Moderate	High	Moderate	High

( Abbreviation: • - Suitable, ∘ - Not Suitable, ∘ - Limited suitability, ■ - Not Recommended, R - Redder,

G - Greener, B - Bluer)


V 1.0D,07/20

Page 1 of 3




# **Coralene Blue SBGL**

#### **Product Performance:**




(Dyeing at different dyebath temperature on polyester fabric at pH 4 adjusted with Levocol 4398)



(Exhaust dyeing different depth at 130°C temperature for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)


# **Thermosol Application:**

9.0 gpl Coralene Blue SBGL on P/C fabric



# pH Sensitivity:

0.90 % Coralene Blue SBGL in exhaust dyeing



Fastness Properties: (Tested on 80D/36F 100% PET Knit dyed by exhaust method)

- Light fastness (ISO 105 B02)
- Light fastness (AATCC 16, Option 3, 20 AFU)
- Sublimation fastness at 0.90% depth (ISO 105 P01, 30 Sec)

Shade change (Rating)					
0.15%	0.30%	0.90%			
5-6	5-6	5			
4.0	4.0	4.0			

Temperature	180°C	190°C	200°C
C.O.S.	4-5	4-5	4-5
Staining on PET	4-5	4	4

v 1.0D,07/20 Page 2 of 3



# **Coralene Blue SBGL**

Fastness Properties: (Tested at 0.90% depth, on 80D/36F 100% PET Knit dyed by exhaust method and post set at 180°C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
<ul> <li>Perspiration Light fastness (ISO 105 B07)</li> </ul>	Acidic	4-5						
<ul> <li>Perspiration Light fastness (ISO 105 B07)</li> </ul>	Alkaline	4-5						
<ul><li>Wash fastness (ISO 105 C06, A2S, )</li></ul>		4	3-4	4-5	3	4	4-5	4
Wash fastness (ISO 105 C06, C2S, )		4	3-4	4	3-4	4	4-5	4-5
• Wash fastness (ISO 105 C10 C, 60°C)		4	3-4	4-5	3-4	4	4-5	4-5
Wash fastness (AATCC 61 Option 2A, 49 <sup>o</sup> C)		4.0	2.0	4.0	1.5	3.5	4.0	3.0
Dry cleaning fastness (ISO 105 D01)		4	4-5	4-5	4-5	4-5	4-5	4-5
Water fastness (ISO 105 E01)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
Sea water fastness (ISO 105 E02)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
Chlorinated water (ISO 105 E03)	20 ppm	4-5						
Chlorinated water (ISO 105 E03)	50 ppm	4						
Perspiration fastness (ISO 105 E04)	Acidic	4-5	4	4-5	4	4-5	4-5	4-5
Perspiration fastness (ISO 105 E04)	Alkaline	4-5	4	4-5	4	4-5	4-5	4-5
Hypochlorite bleach fastness (ISO 105 N01)		4-5						
Peroxide bleach fastness (ISO 105 N02)		4-5		4		3-4		
Crocking fastness (ISO 105 X12, Dry/Wet)				4-5/4-5				
PVC migration (ISO 105 X10)		3 (Staining on PVC film)						
Saliva fastness (DIN 53160)		5 (Staining on filter paper)						

Note:

Disclaimer: This information is provided in good faith, to the best of our knowledge and without liabilities.



# **Colourtex Industries Private Limited,**

Domestic: Tel.: +91 261 2897800/2897801 E mail: sales.surat@colourtex.co.in Export: Tel.: +91 261 2891427 /2897428 E mail: ctx.export@colourtex.co.in

Page 3 of 3 V 1.0D,07/20