

f

### **TECHNICAL INFORMATION**

Sözalprint Corrozione Ready-to-use discharge printing paste

### **PROPERTIES**

I IVOI EIVIIEO		
Component	Acrylic resin based dispersion	
Appearance	White paste	
Odour	Characteristic	
pH(%8)	8.0-9.5	
Ionic Structure	Anionic- nonionic	

# **Application**

Sözalprint Corrozione is ready-to-use printing paste, that developed for discharge printing of fabrics dyed with dischargable dyestuffs. Sözalprint Corrozione could be used on fabrics has lower discharging degree (inferior 5).

Sözalprint Corrozione can be printed with 77 threads/cm pattern. For better discharging degree 43-55 threads/cm pattern printing recommended.

With Sözalprint Corrozione wet-on-wet printing could be applied to fabric. Discharging effect expose with curing and fixing 150-160 °C at 4-5 min.

After curing and fixing application ,washing of printed fabrics with anionic detergent at 40 °C is recommended. Bad odor caused from discharging products could be removed with washing.

### Printing paste recipe

•	1000 a/ka(	1000 g/kg(pH:5-5.5)	
Dyestuff	25-40	g/kg	
Urea	150-200	g/kg	
Discharging product	70-100	g/kg	
Sözalprint Corrozione	up to 1000	g/kg	

<sup>\*\*\*</sup>Shelf life of printing paste is 24 hours after added discharge products.

Printing could be varies depending of different fabric blends due to used discharging product.

## **Storage**

**Storage** :Storage life is 12 months in its original package at room temperature(+5....+35 °C). Sözalprint Corrozione must be protect from excess amount of heat and freeze.

Packing: 120 kg plastic barrels

**Note:** Before usage of Sözalprint Corrozione some preliminary test is recommended for confirmation of clients requests.

Like other anionic chemicals, Sözalprint Corrozione does not compatible with cationic products.

Many of their dyestuffs, pigments and chemicals are patented by Sözal Ltd or its affiliates in numerous industrial countries. ® Trademark registered by Sözal Ltd or Sözal in numerous countries.

The signs ®, \* and + appear only at the first mention of the product.

The information and recommendations presented here were compiled with the utmost care, but cannot be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing conditions.

<sup>\*</sup> Trademark licensed to Sözal Ltd in numerous countries.

<sup>+</sup> Manufacturer's registered trade mark