



## TECHNICAL INFORMATION

### SEGAFIX BK8 LIQ

Formaldehyde-free crosslinking agent to improve polyurethane efficiency of products such as appretane and fluorocarbon

- Can be used in combination with fluorocarbon resins for cotton, cellulosic fibers, synthetic fibers and their mixtures.
- Improves water and oil repellency
- Improves washing and dry cleaning fastness.
- Segafix BK8 Liq. can also be used to increase the washing resistance as a crosslinking agent (based on polyurethane and acrylic resin) in coating pastes.

### Properties

Appearance	Transparent, light yellow liquid
Ionic Character	Nonionic
Ph	6.0-8.0
Viscosity (25°C, cps)	Max 300

## APPLICATION

### The amount of usage

- Application quantity is suitable in usage of 10-12 % Segafix BK8 Liq. by weight based on the resin to be used.
- Fix the optimum prescription at 150°C for 1 min.

### Precautions

#### Storage

6months at room temperature and original packaging

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet