



TECHNICAL INFORMATION

SEGANAL TXT

Levelling–dispersing agent for the dyeing of yarns and PES products specially effective in the dyeing of winding products.

- It is an auxiliary equilibrating agent used in dyeing polyester fibers and specific winding process (bobbin yarns, fabric).
- Increases the penetration and migration of disperse dyes.
- Provides good dispersion of oligomers.
- It has high thermal stability and can be used under pressure up to 135 °C
- Prevents dyestuff strikes by adjusting the dyestuff shot.

PROPERTIES

Appearance	Slightly turbid, yellowish liquid
Ionic character	Anionic
pH	5.0–7.0
Stability	<ul style="list-style-type: none">• hard water limited• electrolyte limited• alkali no
Compatibility	<ul style="list-style-type: none">• anionic products good• non ionic products good <p>We recommend preventive trials.</p>
Foam	Low

APPLICATION

- Seganal TXT the color depending on the status 0.5–1 g/L in the amount of use, for better discharge of dyes from the products a bit more can be added.
- We recommend using of soft water.
- In particular, PES/cotton blended fabrics Segaquest DP dispersing/sequestering also to be added.
- In case of electrolyte in the bath will result in precipitation of the product, avoid dyeing of two fabrics in the same bath.
- Dyeing procedures are recommended as the dyestuff manufacturer.
- It is recommended to check the compatibility of the carrier with the painting bath.

Recipe sample:

Light Colors

- In dye solution; 0.2–0.3 g/L
- In dye bath; 0.2–0.8 g/L

Medium and Dark Colors

- In dye Solution; 0.2–0.3 g/L
- In dye bath; 0.2–0.5 g/L

PRECAUTIONS

Stoge: The storage life in original package at 0–40 °C is 12 months.

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet.