



TECHNICAL INFORMATION

SEGAPRINT WHITE MZS-V

Ready –made paste for textile printing

PROPERTIES

Appearance	White viscous paste
Odor	Slightly ammonia
pH	8.0-10.0
Ionic structure	Anionic-Nonionic

APPLICATION

Segaprint White MZS-V is a high concentration ready-made printing paste obtained by dispersing titanium dioxide and acrylic resin in water-based emulsion.

Segaprint White MZS-V has highly coating properties . For this reason, Segaprint White MZS-V is suitable for printing of dark-toned fabrics. Also Segaprint White MZS-V could be used as in color or by adding pigment printing dyes for pastel colours.

Segaprint White MZS-V has good fastness on cotton fabric surface. For this Segaprint White MZS-V is recommended with adding 10-20 g / kg Fixator LF into for cellulosic and synthetic blend fabrics. After printing and drying , printing of fabrics with Segaprint White MZS-V should be fixed at 150-160 ° C for 3 minutes.

To increase the printability of the Segaprint White MZS-V it is recommended to adding 20-40 g / kg LICOTIL AP into Segaprint White MZS-V under the agitator.

PRECAUTIONS

STORAGE

Storage: The product is stable for 12 months under normal conditions. Protect against frost and keep in closed containers at temperatures between +5 and + 35 ° C away from the heater.

Packaging: 120kg plastic barrel.

Note: Before using our product, we need some tests to determine if it is in line with customer wishes evaluation is recommended.

Like many anionic chemicals, this product is incompatible with cationic products.

Paints, pigments, and most of the chemicals are patented by Sozal Ltd or its subsidiaries in various industrial countries. The information and recommendations presented here have been created with great care, but they may not include every possible situation. These information and recommendations are non-binding guidelines and must be adapted to the conditions in force. Moreover, no liability is accepted for the non-written application areas and methods. Information and protective measures that are required to be specified can be obtained from the Safety Data Sheet.