

Sodecron Red BEL

A non dischargeable and high energy red disperse dye with high light fastness suitable for various applications on polyester

Suitability / Application:

Substrate:

Fiber / Yarn	-	0
Sewing threads	-	●
Piece dyeing	-	●
Micro fibers / fabric	-	■
P/C Blends - Exhaust, 2 bath	-	0
P/C Blends - Continuous	-	■
P/Elastane Blends	-	■
P/W Blends	-	○

Process:

Exhaust dyeing:

Low temperature with carrier	-	○
Carrier dyeing at 110°C	-	○
HT, 130°C	-	●
HT, Alkaline dyeing (buffered at pH 9.5)	-	●

Continuous dyeing	-	●
Printing	-	●

Development method in printing:


Pressure Steaming	-	■
HT Loop Steaming	-	●
Discharge printing	-	
Dischargeable ground	-	○
Discharge resistant illuminant	-	●

Exhaust Dyeing


1.33%



4.00%



8.00%



Dyeing at 130°C for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)

General properties:

C.T.Z.: 95 - 125°C

Leveling at 130°C: Good

Migration: Moderate

pH range for application : 3.0 - 7.0

Dischargeability:(Zinc sulphoxylate formaldehyde) Non dischargeable

Sensitivity to metal (Fe): High


Stripping method: -

Saturation value in HTHP exhaust dyeing: 8.00%

(On 80D/36F polyester knit fabric)

Continuous dyeing

40.0 g/l on P/C cloth



Shade change under artificial light:

D 65	Inc A	F 11 (TL 84)	F02 (CWF)	UL 35
Control	YY	Y	GG	Y


Cross staining on other components of blends in one bath dyeing:

Substrate	CA	PAN	PA	Cellulosic	Wool
Staining in dyebath	High	Moderate	High	Moderate	High
Staining after R.C.	High	Moderate	High	Low	High


(Abbreviation: ● - Suitable, ○ - Not Suitable, 0 - Limited suitability, ■ - Not Recommended, R - Redder,

Sodecron Red BEL

Product Performance:



(Dyeing at different dyebath temperature on polyester fabric at pH 4 adjusted with Levocol 4398)





(Exhaust dyeing different depth at 130°C temperature for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)

Thermosol Application:

40.0gpl Sodecron Red BEL on P/C fabric

pH Sensitivity:

4.00% Sodecron Red BEL in exhaust dyeing



Fastness Properties: (Tested on 80D/36F 100% PET Knit dyed by exhaust method)

- Light fastness (ISO 105 B02)
- Light fastness (AATCC 16, Option 3, 20 AFU)
- Sublimation fastness at 4.00% depth (ISO 105 P01, 30 Sec)

Shade change (Rating)		
0.67%	1.33%	4.00%
6	6	6
4.0	4.0	4.0

Temperature	180°C	190°C	200°C
C.O.S.	4-5	4-5	4-5
Staining on PET	4-5	4	4

Sodecron Red BEL

Fastness Properties: (Tested at 4.00 % depth, on 80D/36F 100% PET Knit dyed by exhaust method and post set at 180°C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
● Perspiration Light fastness (ISO 105 B07)	Acidic	4-5						
● Perspiration Light fastness (ISO 105 B07)	Alkaline	4-5						
● Wash fastness (ISO 105 C06, A2S,)		4	3-4	4-5	3-4	4	4-5	4-5
● Wash fastness (ISO 105 C06, C2S,)		4	3	4	2-3	4	4-5	4
● Wash fastness (ISO 105 C10 C, 60°C)		4	3-4	4	3-4	4	4-5	4-5
● Wash fastness (AATCC 61 Option 2A, 49°C)		4.0	2.5	4.0	2.0	4.0	4.5	3.5
● Dry cleaning fastness (ISO 105 D01)		4	4-5	4-5	4-5	4-5	4-5	4-5
● Water fastness (ISO 105 E01)		4-5	4	4-5	4	4-5	4-5	4-5
● Sea water fastness (ISO 105 E02)		4-5	4	4-5	4	4-5	4-5	4-5
● Chlorinated water (ISO 105 E03)	20 ppm	4						
● Chlorinated water (ISO 105 E03)	50 ppm	4						
● Perspiration fastness (ISO 105 E04)	Acidic	4-5	4	4-5	4	4-5	4-5	4-5
● Perspiration fastness (ISO 105 E04)	Alkaline	4-5	4	4-5	4	4-5	4-5	4-5
● Hypochlorite bleach fastness (ISO 105 N01)		4-5						
● Peroxide bleach fastness (ISO 105 N02)		4-5		4-5		4-5		
● Crocking fastness (ISO 105 X12, Dry/Wet)				4/4-5				
● PVC migration (ISO 105 X10)		3-4	(Staining on PVC film)					
● Saliva fastness (DIN 53160)		5	(Staining on filter paper)					

Note:

Disclaimer: This information is provided in good faith, to the best of our knowledge and without liabilities.