

Sodecron Brilliant Red HP-3BS

A brilliant bluish red disperse dye having excellent wash, light, contact and chlorinated water fastness. Exhibits good build up; serves as a backbone for deep red, maroon shades and as a basic ternary component with Yellow Brown HP -2R and Navy HP - R

Suitability / Application:

Substrate:

Fiber / Yarn	-	●
Sewing threads	-	●
Piece dyeing	-	●
Micro fibers / fabric	-	●
P/C Blends - Exhaust, 2 bath	-	●
P/C Blends - Continuous	-	●
P/Elastane Blends	-	●
P/W Blends	-	○

Process:

Exhaust dyeing:

Low temperature with carrier	-	○
HT, 135°C	-	●
HT, Alkaline dyeing	-	○

Continuous dyeing

	-	●
--	---	---

Printing

	-	●
--	---	---

Development method in printing:

Pressure Steaming	-	●
HT Loop Steaming	-	●

Discharge printing

	-	■
--	---	---

Exhaust Dyeing

0.370%



1.10% (1/1 SD)



2.20%



(Dyeing at 135°C for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)

General properties:

C.T.Z.:	-	110 - 135°C
Leveling at 135°C:	-	Moderate
Migration:	-	Moderate
Recommended pH with buffer system :	-	4.0
Recommended auxiliary:	-	Levocol OA, 3 - 4 g/l
Dischargeability:(Zinc sulphoxylate formaldehyde)	-	Good
Sensitivity to metal (Fe)	-	Low
Stripping method	-	Reductive
Saturation value in HTHP exhaust dyeing (On 80D/36F polyester knit fabric)	-	2.75%

Continuous dyeing

11 g/l on P/C cloth



Shade change under artificial light:

D 65	Inc A	F 11 (TL 84)	F02 (CWF)	UL 35
Control	YY	G	GG	Y

Cross staining on other components of blends in one bath dyeing:


Substrate	CA	PAN	PA	Cellulosic	Wool
Staining in dyebath	High	High	High	Moderate	High
Staining after R.C.	High	High	High	Low	Moderate

(Abbreviation: ● - Suitable, ○ - Not Suitable, ◐ - Limited suitability, ■ - Not Recommended, R - Redder, G - Greener,


Y - Yellower, B - Bluer)

Sodecron Brilliant Red HP-3BS

Product Performance:



(Dyeing at different dyebath temperature on polyester fabric at pH 4 adjusted with Levocol 4398)





(Exhaust dyeing different depth at 135°C temperature for 45 min on polyester fabric at pH 4 adjusted with Levocol 4398)

Thermosol Application: (Pad - Dry - Thermosol)

11.0 gpl Sodecron Red HP-3BS on P/C fabric

pH Sensitivity:

1.10% Sodecron Red HP-3BS in exhaust dyeing



Fastness Properties: (Tested on 80D/36F 100% PET Knit, dyed by exhaust method)

- Light fastness (ISO 105 B02)
- Light fastness (AATCC 16, Option 3, 20 AFU)
- Sublimation fastness 1/1 SD (ISO 105 P01)

Shade change (Rating)		
1/6 SD	1/3 SD	1/1 SD
4-5	5	6
3.5	4.0	4.5

Temperature	180°C	190°C	200°C
C.O.S.	4-5	4-5	4-5
Staining on PET	4-5	4	3-4

Sodecron Brilliant Red HP-3BS

Fastness Properties: (Tested at 1.10% depth, on 80D/36F 100% PET Knit dyed by exhaust method and post set at 180°C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
— Perspiration Light fastness (ISO 105 B07)	Acid	4-5						
— Perspiration Light fastness (ISO 105 B07)	Alkaline	4-5						
— Wash fastness (ISO 105 C10 C, 60°C)		4	4-5	4-5	4-5	4-5	4-5	4-5
— Wash fastness (ISO 105 C06, C2S,)		4	4-5	4-5	4-5	4-5	4-5	4-5
— Wash fastness (AATCC 61 Option 2A,49°C,)		4.0	4.5	4.5	4.5	4.5	4.5	4.5
— M&S C4A, 60°C		4-5	4-5	4-5	4-5	4-5	4-5	4-5
— Adidas Wash fastness, 60°C		4	4	4	3-4	4	4-5	4-5
— Dry cleaning fastness (ISO 105 D01)		4	4-5	4-5	4-5	4-5	4-5	4-5
— Water fastness (ISO 105 E01)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
— Sea water fastness (ISO 105 E02)		4-5	4	4-5	4	4-5	4-5	4-5
— Chlorinated water fastness,(Adidas 5.06, 50 ppm)		4						
— Perspiration fastness (ISO 105 E04,Acid)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
— Perspiration fastness (ISO 105 E04,Alkaline)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
— Burnt gas fumes fastness (ISO 105 G02, 3 cycles)		4-5						
— Hypochlorite bleach fastness (ISO 105 N01)		4-5						
— Peroxide bleach fastness (ISO 105 N02)		4-5		4-5		4-5		
— Mercerization fastness (ISO 105 X04)		4-5						
— PVC migration (ISO 105 X10)		3-4 (Staining on PVC foil)						
— Crocking Fastness (ISO 105 X12, Dry/Wet)		4-5/4						
— Migration during storage (AATCC TM 163)		4.5	4.5	4.5	4.5	4.5	4.5	4.5
— Saliva fastness (DIN 53160)		5 (Staining on filter paper)						

Fastness Properties: (Tested at 4.0% depth, on 100% micro PET Knit (0.5 dpf) dyed by exhaust method and post set at 180°C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
— Light fastness (ISO 105 B02)		4						
— Wash fastness (ISO 105 C06, C2S,)		4	4-5	4-5	4-5	4-5	4-5	4-5
— Wash fastness (AATCC 61 Option 2A,49°C,)		4.0	4.5	4.5	4.5	4.5	4.5	4.5
— Water fastness (ISO 105 E01)		4-5	3-4	4	3	4	4-5	4
— Crocking Fastness (ISO 105 X12, Dry/Wet)		4/4						

Fastness Properties: (Tested at 11.0 g/l depth, on P/C (67/33) blend twill fabric by continuous dyeing method and post set at 180°C for 30 Sec)

		Staining on						
		C.O.S.	Acetate	Cotton	Nylon	Polyester	Acrylic	Wool
— Wash fastness (ISO 105 C06, C2S,)		4	4-5	4-5	4-5	4-5	4-5	4-5
— Wash fastness (AATCC 61 Option 2A,49°C,)		4.0	4.5	4.5	4.5	4.5	4.5	4.5
— Water fastness (ISO 105 E01)		4-5	4-5	4-5	4-5	4-5	4-5	4-5
— Crocking Fastness (ISO 105 X12, Dry/Wet)		4-5/4						

Note:

Disclaimer: This information is provided in good faith, to the best of our knowledge and without liabilities.