

Segenol Yellow ME4GL



- Lemon Yellow with good fastness profile.
- Dischargeable

Substrate Suitability

Cotton	S
Viscose	S
Polyester / Cotton Blend	S
Polyester / Viscose Blend	S
Cotton / Elastane Blends	S

Application method:

Exhaust dyeing:

Dyeing Temperature	60°C & 80°C
--------------------	-------------

Continuous dyeing

Cold Pad Batch	S
Pad-Dry-Pad-Steam	S
E-Control	S
Pad Steam	L.S
Pad-Dry-Thermofix	L.S

General properties:

Dischargeability:	D	
Solubility neutral (gpl) :	80 gpl	
Solubility with 50g/l G. Salt at 50°C :	50 gpl	
Alkali Stability	ASS	Stable
	PLS	Stable
Substantivity	Medium	
Fixation Value	60.00%	
Reactivity	Medium	

Remarks:-

(Abbreviation: S-Suitable, NS - Not Suitable,

ASS - Alkali + Salt + Stability

PLS - Pad Liquor Stability.

R - Redder,

G - Greener,

RR- Much Redder

L.S - Limited Suitability

Exhaust Dyeing on 100% Cotton
interlock knit fabric


3.21%(1/2)



6.4%(1/1)



Cold pad-batch on
mercerised cotton Poplin



32 g/l




64 g/l

Fastness Properties:

Light fastness	1/1.	1/6.					
● Light fastness (ISO 105 B02)- Upto grade 6	5--6	5					
● Light fastness (AATCC 16, Option 3) 20 AFU	4	4					
● Light fastness (AATCC 16, Option 3) 40 AFU	NA	NA					
● Perspiration light fastness (acidic) (Nike Method)	NA	NA					
● Perspiration light fastness (alkaline)(Nike Method)	4	3.5					
● Wash &Wet fastness properties. (1/1 SD.)	CS	CA	CO	PA	PES	PAN	WO
● Wash fastness (ISO 105 C06, C2S,)	4	4--5	4--5	4--5	4--5	4--5	4--5
● Wash fastness (ISO 105 C10 C3, 60°C)	4	4--5	4--5	4--5	4--5	4--5	4--5
● Wash fastness (AATCC 61 Option 2A,49°C,)	4	4.5	4.5	4.5	4.5	4.5	4.5
● Water severe M&S,C6	4--5	4--5	4--5	4--5	4--5	4--5	4--5
● Drycleaning M&S,C-5	4	4--5	4--5	4--5	4--5	4--5	4--5
● Fastness to Oxidative bleach M&S C-10A	2-Off tone						
● Perspiration fastness (M&S C7,Acid)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
● Perspiration fastness (M&S C7,Alkaline)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
● Fastness to Chlorinated water (ISO 105 E03) (20 ppm)	3--4						
● Fastness to Hot pressing ISO 105 X-11-T (immediate ,Wet/Dry)	NA						
● Fastness to Hot pressing ISO 105 X-11-T (after 4hrs,Wet/Dry)	NA						
● Fastness to Burnt gas fumes (ISO 105 G02:1993,1 cycles)	4						
● Crocking Fastness (ISO 105 X12, Dry/Wet)	4--5/3--4						
● Hypochlorite bleaching ISO 105 N01 : 1993	1--2						
● Fastness to Peroxide bleaching ISO 105 N02:1993	2						
● Shade change after Resin finish.	Tr.Greener bluer.						

- **Build up property** (Cotton Knits Interlock
Un-mercerised bleached fabric)




% Stripping with recommended Recipe :


Stripping Method :

Caustic Soda 32.5%	10.-15	ml/l
Hydrosuphite Conc	5	g/l

Heat from 60°C to 90°C in 15 min. hold for 30 min. at 90°C, then rinse neutralisation with Acidic acid (pH 5.5) at Room Temp followed by warm and cold wash



Cross staining on other components of blends in one bath dyeing :



(This information provided is in good faith, to the best of our knowledge and without liabilities)