

Segenol Blue MERL



- Reactive Blue With Good light fastness .
- Neutral Blue as trichromatic Component Suitable with

Application method:

Exhaust dyeing:

Dyeing Temperature	60°C
--------------------	------

Continuous dyeing

Cold Pad Batch	S
Pad-Dry-Pad-Steam	S
E-Control	S
Pad Steam	L.S
Pad-Dry-Thermofix	L.S

General properties:

Dischargeability:	ND	
Solubility neutral (gpl) :	100 gpl	
Solubility with 50g/l G. Salt at 50°C :	80 gpl	
Alkali Stability	ASS	Stable
	PLS	Stable
Substantitivity	Medium	
Fixation Value	81.41%	
Reactivity	High	

Remarks:-

(Abbreviation: S-Suitable, NS - Not Suitable,

ASS - Alkali + Salt + Stability

PLS - Pad Liquor Stability.

R - Redder,

G - Greener,

RR- Much Redder

L.S -Limited Suitability.

Exhaust Dyeing on 100% Cotton
interlock knit fabric

2.35%(1/2)



4.70%(1/1)



9.4%(2/1)



Cold pad-batch on
mercerised cotton Poplin

23.5 g/l



47.g/l



94. g/l




Fastness Properties:

Light fastness	1/1.	1/6.	1/12.				
● Light fastness (ISO 105 B02)- Upto grade 6	5--6	5	5				
● Light fastness (AATCC 16, Option 3) 20 AFU	4.5	4.5	4				
● Light fastness (AATCC 16, Option 3) 40 AFU	4	4	4				
● Perspiration light fastness (acidic) (Nike Method)	4	3.5	3.5				
● Perspiration light fastness (alkaline)(Nike Method)	4	3.5	3.5				
Wash &Wet fastness properties	CS	CA	CO	PA	PES	PAN	WO
● Wash fastness (ISO 105 C06, C2S,)	4	4--5	4--5	4--5	4--5	4--5	4--5
● Wash fastness (ISO 105 C10 C3, 60°C)	4	4--5	4	4	4--5	4--5	4--5
● Wash fastness (AATCC 61 Option 2A,49°C,)	4	4.5	3.5	4.5	4.5	4.5	4.5
● Water severe M&S,C6	4--5	4	3--4	3--4	4--5	4--5	4--5
● Drycleaning M&S,C-5	4	4--5	4--5	4--5	4--5	4--5	4--5
● Fastness to Oxidative bleach M&S C-10A	4 On Tone						
● Perspiration fastness (M&S C7,Acid)	4--5	4	3--4	4	4--5	4--5	4--5
● Perspiration fastness (M&S C7,Alkaline)	4--5	3	2--3	3--4	4	4	4
● Fastness to Chlorinated water (ISO 105 E03) (20 ppm)	3--4						
● Fastness to Hot pressing ISO 105 X-11-T (immediate ,Wet/Dry)	4--5/4--5						
● Fastness to Hot pressing ISO 105 X-11-T (after 4hrs,Wet/Dry)	4--5/4--5						
● Fastness to Burnt gas fumes (ISO 105 G02:1993,1/3 cycles)	4/3--4						
● Crocking Fastness (ISO 105 X12, Dry/Wet)	4--5/3						
● Hypochlorite bleaching ISO 105 N01 : 1993	3--4						
● Fastness to Peroxide bleaching ISO 105 N02:1993	2						
● Shade change after Resin finish.	Much Greener .						

● **Build up property** (Cotton Knits Interlock

Un-mercerised bleached fabric)




% Stripping with recommended Recipe :


Stripping Method :

Caustic Soda 32.5%	10.-15	ml/l
Hydrosuphite Conc	5	g/l

Heat from 60°C to 90°C in 15 min. hold for 30 min. at 90°C, then rinse neutralisation with Acidic acid (pH 5.5) at Room Temp followed by warm and cold wash



Cross staining on other components of blends in one bath dyeing :



(This information provided is in good faith, to the best of our knowledge and without liabilities)