

Segenol Yellow SD3R



- It's bright reactive G.yellow with good light fastness.
- Good build -up in deep shades.

Substrate Suitability

Cotton	S
Viscose	S
Polyester / Cotton Blend	S
Polyester / Viscose Blend	S
Cotton / Elastane Blends	S

Application method:

Exhaust dyeing:

Dyeing Temperature	60°C
--------------------	------

Continuous dyeing

Cold Pad Batch	S
Pad-Dry-Pad-Steam	
E-Control	
Pad Steam	
Pad-Dry-Thermofix	

General properties:

Dischargeability:	ND	
Solubility neutral (gpl) :	150gpl	
Solubility with 50g/l G. Salt at 50°C :	70 gpl	
Alkali Stability	ASS	Stable
	PLS	Stable
Substantitivity	Medium	
Fixation Value	63.00%	
Reactivity	Medium	

Remarks:-

(Abbreviation: S-Suitable, NS - Not Suitable,

ASS - Alkali + Salt + Stability

PLS - Pad Liquor Stability.

R - Redder,

G - Greener,

RR- Much Redder

Exhaust Dyeing on 100% Cotton interlock knit fabric

0.79%(1/2)



1.58%(1/1)



3.16%(2/1)



Cold pad-batch on mercerised cotton poplin

8 g/l



16 g/l



32 g/l






Fastness Properties:

Light fastness	1/1.	1/6.					
Light fastness (ISO 105 B02)- Upto grade 6	6	5--6					
Light fastness (AATCC 16, Option 3) 20 AFU	4--5	4--5					
Light fastness (AATCC 16, Option 3) 40 AFU	4	4					
Perspiration light fastness (acidic) (Nike Method)	NA						
Perspiration light fastness (alkaline)(Nike Method)	4--5	4--5					
Wash &Wet fastness properties	CS	CA	CO	PA	PES	PAN	WO
Wash fastness (ISO 105 C06, C2S,)	4	4--5	4--5	4--5	4--5	4--5	4--5
Wash fastness (ISO 105 C10 C3, 60°C)	4	4--5	4--5	4--5	4--5	4--5	4--5
Wash fastness (AATCC 61 Option 2A,49°C,)	4	4--5	4--5	4--5	4--5	4--5	4--5
Water severe M&S,C6	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Drycleaning M&S,C-5	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Fastness to Oxidative bleach M&S C-10A	4--5 On tone						
Perspiration fastness (M&S C7,Acid)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Perspiration fastness (M&S C7,Alkaline)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Fastness to Chlorinated water (ISO 105 E03) (20 ppm)	3						
Fastness to Hot pressing ISO 105 X-11-T (immediate)	4--5/4--5						
Fastness to Hot pressing ISO 105 X-11-T (after 4hrs)	4--5/4--5						
Fastness to Burnt gas fumes (ISO 105 G02:1993) (1 &3 cycles)	4						
Croaking Fastness (ISO 105 X12, Dry/Wet)	4--5/3--4						
Hypochlorite bleaching ISO 105 N01 : 1993	4						
Fastness to Peroxide bleaching ISO 105 N02:1993	4						
Shade change after Resin'finish.	Greener bluer						

- Build up property** (Cotton Knits Interlock Un-mercerised bleached fabric)




% Stripping with recommended Recipe :


Stripping Method :

Caustic Soda 32.5%	10.-15	ml/l
Hydrosuphite Conc	5	g/l

Heat from 60°C to 90°C in 15 min. hold for 30 min. at 90°C, then rinse neutralisation with Acidic acid (pH 5.5) at Room Temp followed by warm and cold wash



Cross staining on other components of blends in one bath dyeing :



(This information provided is in good faith, to the best of our knowledge and without liabilities)