

Segenol Yellow RP-N



- High light fast reactive yellow with good perspiration light fastness and weathering fast
- Good Oxidative bleach Fast

Substrate Suitability

Cotton	S
Viscose	S
Polyester / Cotton Blend	S
Polyester / Viscose Blend	S
Cotton / Elastane Blends	S

Application method:

Exhaust dyeing:

	Dyeing Temperature	60°C
--	--------------------	------

Continuous dyeing

	Cold Pad Batch	S
	Pad-Dry-Pad-Steam	N.A
	E-Control	N.A
	Pad Steam	N.A
	Pad-Dry-Thermofix	N.A

General properties:

Dischargeability:		ND
Solubility neutral (gpl) :		150gpl
Solubility with 50g/l G. Salt at 50°C :		100 gpl
Alkali Stability	ASS	Stable
	PLS	Stable
Substantitivity		Medium
Fixation Value		65.73%
Reactivity		Medium

Remarks:-

(Abbreviation: S-Suitable, NS - Not Suitable,

ASS - Alkali + Salt + Stability

PLS - Pad Liquor Stability.

R - Redder,

G - Greener,

RR- Much Redder

L.S -Limited Suitability


N.A - Not Analysed .

Exhaust Dyeing on 100% Cotton
interlock knit fabric


1.50%(1/2)



3.00%(1/1)



6.00%(2/1)



Cold pad-batch on
mercerised cotton Poplin



15 g/l



30 g/l




60 g/l

Fastness Properties:

Light fastness	1/1.	1/6.	1/12.	1/24.			
Light fastness (ISO 105 B02)- Upto grade 6	6	5	5	5			
Light fastness (AATCC 16, Option 3) 20 AFU	4	4	4	4			
Light fastness (AATCC 16, Option 3) 40 AFU	3.5	3.5	3.5	3.5			
Perspiration light fastness (acidic) (Nike Method)	4	4	4	3.5			
Perspiration light fastness (alkaline)(Nike Method)	4	3.5	3.5	3.5			
Fastness to Weathering ISO105B04 (Grade-6)	4	4	4				
Wash &Wet fastness properties.(1/1 SD.)	CS	CA	CO	PA	PES	PAN	WO
Wash fastness (ISO 105 C06, C2S,)	4	4--5	4--5	4--5	4--5	4--5	4--5
Wash fastness (ISO 105 C10 C3, 60°C)	4	4--5	4--5	4--5	4--5	4--5	4--5
Wash fastness (AATCC 61 Option 2A,49°c,)	4	4--5	4--5	4--5	4--5	4--5	4--5
Water severeM&S,C6	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Drycleaning M&S,C-5	4	4--5	4--5	4--5	4--5	4--5	4--5
Fastness to Oxidative bleach M&S C-10A	4 On Tone						
Perspiration fastness (M&S C7,Acid)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Perspiration fastness (M&S C7,Alkaline)	4--5	4--5	4--5	4--5	4--5	4--5	4--5
Fastness to Chlorinated water (ISO 105 E03,20/50 ppm)	3--4/3						
Fastness to Hot pressing ISO 105 X-11-T (immediate, Wet/Dry)	4--5/4--5						
Fastness to Hot pressing ISO 105 X-11-T (after 4hrs,Wet/Dry)	4--5/4--5		4	Damp-4--5			
Fastness to Burnt gas fumes (ISO 105 G02:1993,1 &3 cycles)	3/3.						
Crocking Fastness (ISO 105 X12, Dry/Wet)	4--5/3--4						
Hypochlorite bleaching ISO 105 N01 : 1993	3--4						
Fastness to Peroxide bleaching ISO 105 N02:1993	4		4--5	Viscose-4--5			
Colour fastness to Saliva & Perspiration Part-1 Saliva	5						
LF BG B82 10:1 Part -2 -Perspiration	5						
Shade change after Resin finish.	Much Greener bluer duller.						

- ☐ Build up property (Cotton Knits Interlock
Un-mercerised bleached fabric)





% Stripping with recommended Recipe :

Stripping Method :


Caustic Soda 32.5%

10.-15 ml/l

Hydrosuphite Conc

5 g/l

Heat from 60°C to 90°C in 15 min. hold for 30 min. at 90°C, then rinse neutralisation with Acidic acid (pH 5.5) at Room Temp followed by warm and cold wash



Cross staining on other components of blends in one bath dyeing :



(This information provided is in good faith, to the best of our knowledge and without liabilities)